



HexForce® 00235 1050 TF970

E GLASS FABRIC

Product Data

Textile Reinforcement for High Performance Composite

HexForce® reinforcements are available in a range of weave styles – from woven fabrics to multiaxials and specialties that offers a range of globally certified aerospace / industrial products in carbon, glass and aramid and specialty fibers that we sell under the HexForce® trademark.

DESCRIPTION

April / 2015

Type of yarns	Warp : EC9 34 Weft : EC9 34	
Nominal weight	87 g/m ²	2.57 oz/sqy ²
Weave style	PLAIN WEAVE	
Width	1050 mm	41.3 in
Finish type	TF970	
Finish description		

CHARACTERISTICS

Nominal construction	Warp : 12 yarn/cm Weft : 12.5 picks/cm	30.7 yarn/in 32 picks/in
Weight distribution	Warp : 49 % Weft : 51 %	
Thickness (*)	0.06 mm	0.002 in

*NB : The above average values are obtained with epoxy laminate at 55% of fibres in volume.

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms.

© Copyright Hexcel



For European sales office telephone numbers and a full address list,
please go to : <http://www.hexcel.com/contact/salesoffices>