



HexForce® 01184 0800 TF970 CLEAR
E GLASS FABRIC

Product Data

Textile Reinforcement for High Performance Composite

HexForce® reinforcements are available in a range of weave styles – from woven fabrics to multiaxials and specialties that offers a range of globally certified aerospace / industrial products in carbon, glass and aramid and specialty fibers that we sell under the HexForce® trademark.

DESCRIPTION

April / 2015

Type of yarns	Warp : EC9 68 X 2 Weft : EC9 136	
Nominal weight	205 g/m ²	6.05 oz/sqy ²
Weave style	PLAIN WEAVE	
Width	800 mm	31.5 in
Finish type	TF970 CLEAR	
Finish description		

CHARACTERISTICS

Nominal construction	Warp : 7.4 yarn/cm Weft : 7.2 picks/cm	18.9 yarn/in 18.4 picks/in
Weight distribution	Warp : 51 % Weft : 49 %	
Thickness (*)	0.15 mm	0.006 in

*NB : The above average values are obtained with epoxy laminate at 55% of fibres in volume.

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms.

© Copyright Hexcel



For European sales office telephone numbers and a full address list,
please go to : <http://www.hexcel.com/contact/salesoffices>